

ITEM 10559.9001 M - ANTI-GRAFFITI PROTECTIVE COATING FOR CONCRETE SURFACES

DESCRIPTION

Under this item, the Contractor shall clean, furnish and place anti-graffiti protective coating on noise barrier walls, retaining walls, bridge structures, barriers, or other concrete surfaces at locations indicated in the contract documents or approved by the EIC.

The Contractor shall apply the protective coating on selected surfaces within the limits in the contract documents which are visible from parkways, expressways, service roads, or various State highways. In addition, the Engineer may order that certain areas receive increased coverage or new locations be added.

This specification is not intended to apply this material to reflectorized sign surfaces.

MATERIALS

The protective coating shall be a breathable, one component clear silicone rubber based formulation designed as an anti-graffiti solution for concrete surfaces.

The Contractor shall provide the manufacturer's product literature including surface preparation data, mixing, application, spread rates, storage and Volatile Organic Compounds (VOC) compliance certification.

All materials are to be approved by the Engineer and the Regional Landscape Architect before any work can begin.

CONSTRUCTION DETAILS

1. The selected surfaces shall be thoroughly cleaned of dust, dirt, grease, oil, loose materials or other objectionable materials before applying the protective coating. No sandblasting will be allowed. Anti-graffiti coating shall be applied as soon as practicable after cleaning is completed. If in the opinion of the Engineer, the surface has become soiled, or otherwise contaminated, prior to the application of the protective coating, the surface shall be recleaned at no additional cost to the State.
2. Surface and material temperatures shall be a minimum of 4°C or as recommended by the manufacturer.
3. Materials shall be applied by brush, roller or low pressure spray. The rolling shall be done at such a pace that no spinning of the roller or throwing off of protective coating material

ITEM 10559.9001 M - ANTI-GRAFFITI PROTECTIVE COATING FOR CONCRETE SURFACES

occurs when the roller is lifted from the surface. Coverage rate shall be as recommended by the manufacturer and as approved by the Engineer.

4. The protective coating shall be applied in a uniform manner to evenly coat all pores and textured areas. Extremely textured or porous surfaces will require a second coat. Unless otherwise designated by the Engineer, the protective coating shall be applied from column to column, post to post, and from bottom to a height of 2.5 m for noise barrier wall panels, and from joint to joint or scoremark to scoremark and from bottom to a height of 2.5 m for abutments, walls and other surfaces.
5. A test panel 1.5 m x 1.5 m shall be provided and coated to insure suitability, number of coats required and desired results. The test panel application and results shall be inspected and approved by the Engineer and the Regional Landscape Architect.
6. All work must conform to the OSHA standards referred to in Subsection 107-05 of the Standard Specifications.

METHOD OF MEASUREMENT

This work will be measured by the number of square meters of surface covered with the anti-graffiti coating, applied in accordance with this specification. Test panels prepared under this item will not be measured for payment.

BASIS OF PAYMENT

The unit price bid per square meter shall include the cost of furnishing all labor, materials and equipment necessary to prepare the surfaces and apply the coating in accordance with the Contract Documents and as directed by the Engineer. The cost of providing test panels shall also be included in the price bid for this item.

There will be no payment for applying anti-graffiti coatings on surfaces that are not within the location limitations stated above.