

**ITEM 10563.0215 M - PRESTRESSED CONCRETE BOX BEAM UNITS WITH CURVED SOFFIT**

**DESCRIPTION:**

This work shall consist of furnishing and placing prestressed box beam units with curved soffit, as specified in the contract documents.

**MATERIALS:**

**Prestressed Units:** The Contractor shall notify the Deputy Chief Engineer Structures (D.C.E.S.) of the source of prestressed units for approval within (7) days after the award of the contract. Prestressed concrete box beam units with curved soffit shall meet the requirements of the New York State Prestressed Concrete Construction Manual (P.C.C.M.).

**Transverse Tie Rods or Strands:** Refer to P.C.C.M. Section 400.

**Shear Key Material:** Refer to P.C.C.M. Section 400.

**Anchorage Blockout Grout:** Refer to P.C.C.M. Section 400.

**Penetrating Sealers:** The protective sealer used on concrete surfaces shall appear on the Department's Approved List and shall meet the requirements of Standard Specifications Construction and Materials Section 717-03 Penetrating Type Protective Sealers. In addition the penetrating sealer shall either use alcohol as a carrier or use no carrier.

**CONSTRUCTION DETAILS:**

The requirements of the P.C.C.M. shall apply.

**Coating of Concrete Units:** All concrete units shall be coated on all surfaces with a penetrating sealer. The surfaces must be prepared by water, shot, or sand blasting, removing all laitance, loose particles, etc. Prior to application of the sealer, the surfaces will be allowed to dry for 24 hours after an accelerated cure, 72 hours after a non-accelerated cure, which shall include a minimum of 24 hours of drying time after water blasting. All surface preparation work shall be completed and approved by the Inspector, before sealer application can commence.

- A. Weather Limitations:** Sealer materials shall not be applied during wet weather conditions, or if, in the opinion of the Inspector, adverse weather conditions are anticipated within twelve (12) hours of completion of sealer application. Ambient and surface temperatures shall be a minimum of 4 degrees C during application and until the sealed concrete is dry to the touch. Application by spray methods will not be permitted during windy conditions.

**ITEM 10563.0215 M - PRESTRESSED CONCRETE BOX BEAM UNITS WITH CURVED SOFFIT**

- B. Sealer Application:** The sealer shall be used as supplied by the Manufacturer without thinning or alteration, unless specifically required in the Manufacturer's instructions. Thorough mixing of the sealer before and during its use shall be accomplished as recommended by the Manufacturer. Equipment for sealer application shall be clean of foreign materials and approved by the Inspector before use. A minimum of two (2) coats of the sealer shall be applied to achieve uniform coverage. The total quantity of sealer applied by each coat shall be equal to the quantity required at the application rate specified in the Approved List. Each coat shall be allowed to dry before the next coat is applied. On sloping and vertical surfaces, sealer application shall progress from bottom to top. Care shall be taken to ensure that the entire surface of the concrete is covered and all pores filled.

**METHOD OF MEASUREMENT:**

The quantity to be paid for under this work will be the number of square meters of plan area of each prestressed unit installed. Plan area is defined as the area bounded by the centerline of bearings and the outer edge of each prestressed unit. No deductions will be made for chamfers, or shear keys, or notch cuts. Space between the units shall not be included in any measurement.

**BASIS OF PAYMENT:**

The unit price bid for these units shall include all labor, materials and equipment necessary to complete the work except that bearings will be paid for under their respective items.

Damaged units which cannot be satisfactorily repaired or which do not meet dimensional and camber tolerances shall be replaced by the Contractor at no cost to the State.

Progress payment will be made when each unit is furnished and placed in accordance with the plans and specifications exclusive of preparing and filling joints. Payment will be made at the unit price bid for 90% of the quantity properly placed, less any payment made under subsection 109-04. The balance of the quantity will be paid for upon completion of the work. The completion of work will include the correct preparation and filling of the joints as well as the tightening of transverse ties.